



**Europäisches
Patentamt**

**European
Patent Office**

**Office européen
des brevets**

REC'D 10 FEB 2004

WIPO

PCT

Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

03000120.0

BEST AVAILABLE COPY

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts:
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

PCT/EP03 / 1 3 8 5.5

Anmeldung Nr:
Application no.: 03000120.0
Demande no:

Anmeldetag:
Date of filing: 02.01.03
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Teijin Twaron B.V.
Westervoortsedijk 73
6827 AV Arnhem
PAYS-BAS

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se référer à la description.)

Aramid filament yarn provided with a conductive finish

In Anspruch genommene Priorität(en) / Priority(ies) claimed /Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

D01F/

Am Anmeldetag benannte Vertragsstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL PT SE SI SK

ARAMID FILAMENT YARN PROVIDED WITH A CONDUCTIVE FINISH

The invention pertains to an aramid filament yarn provided with a conductive finish, to a method of making such yarn, and to the use of said yarn.

A common problem of yarns is breaking of the yarn when used in certain
5 applications. Yarn breaks may occur as a result of over-loading, fatigue, or wear. Ground cable damage may also occur as a result of damage caused by rodents. In elevator cables breakage of cables is a serious safety problem. It is known to add to aramid reinforce elevator cables, for example, one or more carbon yarns or metal wire as a break
10 detector. Such treated aramid reinforced cables, however, do not have the same mechanical characteristics as cables made of untreated aramid yarns only. Moreover, the breaking characteristics of such carbon yarn or metal wire is different from the breaking characteristics of aramid yarn, thereby hampering accurate indication of breaking danger of the aramid reinforced cable. The other mechanical properties of non-aramid yarns in
15 comparison to the main reinforcing material of the cable complicates the predictability of a cable breakage considerably. It would be an advantage to provide aramid yarn having sufficient conductive properties and nevertheless having the same mechanical characteristics as the untreated aramid yarns in the cable.

Some solutions to the above problems are proposed. In WO 9748832 the yarn was
20 coated with a metal such as nickel with an acid. Such treatment provides metalized yarns, the fiber surfaces of which may be damaged by the acid treatment, leading to decrease of tenacity and/or elongation properties. In WO 9325748 a process was disclosed for treating aramid fibers with a dispersion of particulate graphite material in a swelling solvent. Also using this method bears the risk of damaging the fiber surface. Moreover, both methods
25 are very complicated, time consuming, and therefore costly.

The present invention therefore provides in a solution of the above problems, using a simple procedure that is no time consuming, cheap, and without any risk of damaging the fibers. It was found that an aramid filament yarn provided with a finish comprising > 1.5
30 wt.% of an organic substance with a conductivity of > 4 mS/cm, measured as a 50 wt.% finish composition in water at 20°C, having a specific electric resistance of the yarn < $2.5 \cdot 10^4$ Ohm.cm, possesses a sufficient conductivity to be used as a breaking detector,

without affecting its mechanical properties. This is a substantial advantage over the use of, for example, a carbon yarn or a metal wire as break detector in aramid reinforced elevator cables. The conductivity of the organic substance treated and damaged yarn is reduced as a result of breaks caused by wear or fatigue and provides information to the user on the remaining lifetime of the cable. The conductivity of a yarn or a cable can be determined with a resistancy or multimeter.

When finishes comprising a conductive organic substance (COS) are applied onto aramid filament yarn, the electrical yarn resistance thereof is reduced. Depending on the amount of finish and on the conductivity of the applied organic substance, the treated yarn can be used as such, or in combination with untreated aramid filament yarn as an early break detector in (elevator, bearer, ground) cables, or for accessories (brushes, rollers) which have to lay on or to eliminate static electricity in, for example, record players, magnetic tapes, compact disks, and the like.

The conductive organic substance can be applied onto wet or dried yarn as a spin-finish (before or after the drying, as such or diluted with a solvent such as water) in the spinning process or in a separate process step at a relatively high yarn speed.

Aramid filament yarns treated with > 2 wt. % of a conductive organic substance with a conductivity of > 30 mS/cm are preferred. More preferred are yarns treated with > 2 % of a conductive organic substance with a conductivity of > 41 mS/cm. The specific electric resistance of the yarn is preferably < $2 \cdot 10^3$ Ohm.cm, more preferably < 10^3 Ohm.cm. particularly suitable amounts of COS are within the range 3 to 12 wt.%, more preferably within the range 4-9 wt.%. The wt.% is relative to the total weight of the yarn without finish.

Suitable organic substances that are suitable for use in the invention are salts or materials having statically chargeable acid or base groups. Materials with acid groups have preferably carboxylate, phosphonate or sulfonate groups. Materials with base groups have preferably amine groups.

Particularly preferred materials are fatty acids, carbonic acids, (cyclo)alkyl phosphates, (cyclo)alkyl phosphonates, (cyclo)alkyl sulfates, (cyclo)alkyl sulfonates, imidazoline derivatives and polymers such as poly(diallyldimethylammonium chloride), and the like.

The aramid yarns preferably are made of poly(p-phenylene terephthalamide) (PPDT), but may also contain minor amounts of other monomers.

The COS is applied onto the yarn by conventional methods known in the art. The COS can be applied in solution. The solvent may be any suitable solvent, such as alcohol, ether, tetrahydrofuran, acetone, benzene, toluene, ethyl acetate, dichloromethane and the

like. Most preferably the COS is applied as an aqueous solution. Some COS's are purchased as a water-containing product that can be applied as such.

- 5 The suitable amount of COS to be applied can very easily be determined by a simple conductivity measurement, which as such is known in the art. When the conductivity of the COS or the solution of the COS is determined, a skilled person can easily apply the required amount of finish as needed for the specific use.

Procedure for the determination of the conductivity of a finish

- 10 A suitable procedure to determine the conductivity of a finish composition according to the invention is as follows.

A sufficient amount of the aqueous finish solution (50 wt.% of water and 50 wt.% of COS) to be tested is poured into a beaker. Subsequently, the conductivity of this solution is determined according DIN norm 38404 Teil 8 (9.1985) at a temperature of 20°C.

- 15 When the finish containing the COS has a lower or higher water content than 50 wt.%, the concentration of the finish solution should be adjusted to 50 wt.% by respectively the addition of demineralized water or the evaporation of water by heating on a hot plate under stirring at an elevated temperature below 100°C. For the measurement of the conductivity a conductivity meter type LF 537 of the Wissenschaftlich-Technische
20 Werkstätten GmbH, Weilheim, Germany was used.

The water content of the finish solution was determined by the Karl Fischer method. An exact description of the determination of water via Karl Fischer reagent is given in "Karl Fischer Titration, Methoden zur Wasserbestimmung" by Eugen Scholz, Springer-Verlag 1984.

25

Procedure for the determination of the specific electrical resistance

- For the determination of the specific electrical resistance of the aramid yarns a sample-holder consisting of two copper bars separated by two polytetrafluorethylene rods was
30 used. The mutual distance of the bars is 52 mm. The yarn to be tested is wound a number of times (preferably between 3 and 7) times around the two copper bars which are connected with a DC high voltage power source and a Keithley electrometer. With the Keithley electrometer the electrical current was determined after a voltage of 500 V was applied over the copper bars at 20°C and 65% relative humidity. The specific electrical
35 resistance of the yarn was calculated based on Ohm's law, the yarn length between the copper bars, the number of yarn connections, and the cross-section area of the yarn.

The invention is further illustrated with the following non-limitative examples.

Example 1

This example illustrates the procedure of applying a finish containing a conductive organic substance (COS) to a wet, not previously dried, yarn in an operation integrated with the spinning process. A spinning mass was prepared by mixing concentrated (99.8 wt.%) sulfuric acid snow with powdered poly-p-phenylene terephthalamide. The spinning mass was de-aerated, heated to 90°C in a double-screw extruder and fed to a spinneret via a filter and a spinning pump. The spinneret had 1000 orifices of 59 micrometer in diameter. The spinning mass was extruded through the spinning orifices and thereafter successively passed through an air zone of 8 mm in length and a coagulation bath. This bath was a dilute solution of sulfuric acid in water (about 19% by weight) having a temperature of 5°C. The filament bundle thus formed successively passed through a neutralization bath containing a dilute sodium carbonate solution and a washing bath in which the filaments were thoroughly washed with water of about 75°C. Excess adhering water was removed with the aid of a squeeze roller pair. Next, the non-dried bundle of filaments was provided with an aqueous finish containing a COS with the aid of a liquid applicator and a feed pump. Next the yarn was passed over a series of 3 drying drums (6 wraps of 160°C, 6 wraps of 180°C, 4 wraps of 200°C). The yarn was in contact with the surface of the drums for 5-6 seconds in all. Subsequently, the yarn was passed over a transport drum (4 wraps of about 20°C) and was wound into a package at a speed of 400 m/min. The yarn obtained had a linear density of 1610 dtex. The following process conditions were varied (table A and B):

- a) the composition of the finish containing the COS
- b) the amount of COS on yarn

Table A Aqueous finishes containing conductive organic substances

Finish concentration in wt.%	Finish composition code			
	a1 20	b1 20	c1 20	d1 20
COS in solution (%)				
Afilan V4855 (37.6%)	53,2	37,2		
Afilan PTU		6,0		
PolyDADMAC (42.4%)			47,1	
Tallopol ACF (50.5%)				39,6
Demineralized water	46,8	56,8	52,9	60,4

Afilan V4855 is an alkane phosphonate, potassium salt, ex-Clariant GmbH, Frankfurt, Germany.

Afilan PTU is an ethoxylated and propoxylated oleic acid, CH₃-capped, ex-Clariant GmbH, Frankfurt, Germany.

5 PolyDADMAC is the abbreviation of poly(diallyldimethylammonium chloride) with a low mol weight; catalog nr. 62237-6, supplier Aldrich Chemical Company, Inc., Milwaukee, USA.

Tallopol ACF is a product mixture of potassium and sodium salts of carbonic acids, ex-Stockhausen, Krefeld, Germany.

10

Table B The specific electrical resistance

Experiment No.	1A	1B	1C	1D	1E
Finish composition applied with applicator	a1	b1	b1	c1	d1
COS amount on yarn (wt.%)	3,0	3,0	4,0	4,0	4,0
Conductivity of a 50 wt.% finish composition in mS/cm at 20°C	42,6	43,7	43,7	45,4	215,0
Specific electrical resistance of the yarn in Ohm.cm	3,5E+03	6,5E+03	2,8E+03	2,8E+03	6,8E+02

Comparative Example 1

15 This comparative example relates to an experiment in which the yarn of Example 1 was provided with 0.9% of a non-ionic finish normally used for the spinning of Twaron® yarns. The conductivity of the finish solution (50 wt.%) was 0.009 mS/cm. The obtained yarn showed a specific electrical resistance of 7.2E+07 Ohm.cm.

Example 2

20 This example illustrates the procedure of applying a finish containing a conductive organic substance (COS) to a dried yarn in an operation integrated with the spinning process. The spinning mass of Example 1 was extruded through a spinneret which had 2000 orifices of 59 micrometer in diameter and was thereafter successively passed through the same air zone, coagulation, neutralization, and washing bath as described in Example 1. Excess
25 adhering water was removed with the aid of a squeeze roller pair. Next, the yarn was passed over a series of 3 drying drums (6 wraps of 160°C, 6 wraps of 180°C, 4 wraps of 250°C). The yarn was in contact with the surface of the drums for about 7 seconds in all. Next, the completely dried bundle of filaments was provided with an aqueous finish containing a COS with the aid of a liquid applicator and a feed pump. Subsequently, the

yarn was passed over a transport drum (4 wraps of about 20°C) and was wound into a package at a speed of 300 m/min. The yarn obtained had a linear density of 3220 dtex.

The following process conditions were varied (table C and D):

- 5 a) the composition of the finish containing the COS
b) the amount of COS on yarn
c) the concentration of the finish solution

Table C Aqueous finishes containing conductive organic substances

Finish concentration in wt. %	Finish composition code		
	a2	b2	d2
	37,6	46,3	50
COS in solution (%)			
Aflon V4855 (37.6%)	100,0	86,1	
Aflon PTU		13,9	
Tallopel ACF (50.5%)			99,0
Deminerlized water			1,0

Table D The specific electrical resistance

Experiment No.	2A	2B	2C
Finish composition applied with applicator	a2	b2	d2
COS amount on yarn (wt. %)	3,0	3,5	2,5
Conductivity of a 50 wt. % finish composition in mS/cm at 20°C	42,6	43,7	215,0
Specific electrical resistance of the yarn in Ohm.cm	7,8E+03	7,2E+03	9,6E+02

Example 3

This example illustrates the application of a finish containing a conductive organic substance (COS) to a dried yarn not directly coupled to the spinning process.

Commercially available Twaron® 2200 (1610 dtex/f 1000) yarn was subjected to the following treatments. The yarn package was rollingly unwound while successively passing the yarn over a liquid applicator, through a steam box (temperature 240°C, residence time 8 seconds) and finally wound into a package at a speed of 75 m/min. With the liquid

applicator and a feed pump, the yarn was coated with the finishes mentioned in table E and F. The following process conditions were varied:

a) the composition of the finish containing the COS

b) the amount of COS on yarn

5 c) the concentration of the finish solution

Table E Aqueous finishes containing conductive organic substances

Finish concentration in wt. %	Finish composition code			
	a3 15	d3 10	d4 15	d1 20
COS in solution (%)				
Afilan V4855 (37.6%)	40,0			
Tallopel ACF (50.5%)		19,8	29,7	39,6
Demineralized water	60,0	80,2	70,3	60,4

Table F The specific electrical resistance

Experiment No.	3A	3B	3C	3D
Finish composition applied with applicator	a3	d3	d4	d1
COS amount on yarn (wt. %)	2,5	2,0	3,0	4,0
Conductivity of a 50 wt. % finish composition in mS/cm at 20°C	42,6	216,0	215,0	215,0
Specific electrical resistance of the yarn in Ohm.cm	3,9E+03	2,9E+03	1,8E+03	8,8E+02

10 Example 4

This example illustrates the application of a finish containing a conductive organic substance (COS) to a dried yarn not directly coupled to the spinning process.

15 Commercially available Twaron® 2200 (3220 dtex/f 2000) yarn was subjected to the following treatments. The yarn package was unwound while successively passing the yarn over a double rotating kiss-roll and through a hot air oven (temperature 180°C, residence time 18 seconds) and was finally wound into a package at a speed of 100 m/min. With the

double kiss-roll the yarn was coated with the finishes mentioned in table G and H. The following process conditions were varied:

- a) the composition of the finish containing the COS
- b) the amount of COS on yarn
- c) the concentration of the finish solution

5

Table G Aqueous finishes containing conductive organic substances

Finish concentration in wt. %	Finish composition code	
	a1	d4
	20	15
COS in solution (%)		
Afilan V4855 (37.6%)	53,2	
Tallopol ACF (50.5%)		29,7
Demineralized water	46,8	70,3

Table H The specific electrical resistance

Experiment No.	4A	4B
Finish composition applied with applicator	a1	d4
COS amount on yarn (wt.%)	10,3	5,6
Conductivity of a 50 wt.% finish composition in mS/cm at 20°C	42,6	215,0
Specific electrical resistance of the yarn in Ohm.cm	3,5E+03	1,2E+03

10

Example 5

This example illustrates the application of a finish containing a conductive organic substance (COS) to a dried and finish-free yarn not directly coupled to the spinning process. A package of finish-free Twaron® (1610 dtex/f 1000) yarn was subjected to the following treatments. The yarn package was unwound while successively passing the yarn over a liquid applicator, through a hot air oven (temperature 90°C, residence time 32 seconds) and was finally wound into a package at a speed of 50 m/min. With the liquid

15

applicator and a feed pump, the yarn was coated with the finishes mentioned in table K and L. The following process conditions were varied:

- a) the composition of the finish containing the COS
- b) the amount of COS on yarn
- c) the concentration of the finish solution

Table K Aqueous finishes containing conductive organic substances

Finish concentration in wt. %	Finish composition code		
	e1 20	f1 32	g1 20
COS in solution (%)			
Leomin AN	20,0	16,0	
Leomin OR		16,0	
Atlas G3634a			20,0
Demineralized water	80,0	68,0	80,0

Leomin AN is an ethyl octane phosphonate, potassium salt; ex Clariant GmbH, Frankfurt, Germany.

Leomin OR is a polyglycol ester of a fatty acid, ex Clariant GmbH, Frankfurt, Germany.
Atlas G3634a is an imidazoline derivate, quarternized, ex Uniqema, Middlesbrough, England.

Table L The specific electrical resistance

Experiment No.	5A	5B	5C
Finish composition applied with applicator	e1	f1	g1
COS amount on yarn (wt.%)	5,0	8,0	5,0
Conductivity of a 50 wt.% finish composition in mS/cm at 20°C	40,8	15,2	4,7
Specific electrical resistance of the yarn in Ohm.cm	2,2E+03	5,6E+03	2,2E+04


Claims

1. An aramid filament yarn provided with a finish comprising > 1.5 wt.% of an organic substance with a conductivity of > 4 mS/cm, measured as a 50 wt.% finish composition in water at 20°C, having a specific electric resistance of the yarn < $2.5 \cdot 10^4$ Ohm.cm.
2. The aramid filament yarn of claim 1 provided with a finish comprising > 2 wt.% of an organic substance with a conductivity of > 30 mS/cm, measured as a 50 wt.% finish composition in water at 20°C, having a specific electric resistance of the yarn < $2 \cdot 10^3$ Ohm.cm.
3. The aramid filament yarn of claim 1 or 2 provided with a finish comprising > 2 wt.% of an organic substance with a conductivity of > 41 mS/cm, measured as a 50 wt.% finish composition in water at 20°C, having a specific electric resistance of the yarn < 10^3 Ohm.cm.
4. A method of making the yarn of claim 1 having a specific electric resistance of the yarn < $2.5 \cdot 10^4$ Ohm.cm, comprising bringing a solution of an organic substance onto the aramid yarn such as to obtain > 1.5 wt.% of the substance relative to the total weight of the yarn without the finish, characterized in that the organic substance has a conductivity of > 4 mS/cm, measured as a 50 wt.% finish composition in water at 20°C.
5. Use of the yarn of claim 1 in conductive aramid-containing materials.
6. Use of the yarn of claim 1 in lift cables.
7. Use of the yarn of claim 1 in fibers for transporting electric current or for eliminating static electricity.

Abstract:

The invention pertains to an aramid filament yarn provided with a finish comprising > 1.5 wt.% of an organic substance with a conductivity of > 4 mS/cm, measured as a 50 wt.%
5 finish composition in water at 20°C, having a specific electric resistance of the yarn < $2.5 \cdot 10^4$ Ohm.cm, and to a method of making said yarn.

PCT Application
PCT/EP2003/013855



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.